

ISOLAC DUCO

Izdržljiva, emajl boja za metalne površine. Završni izgled - Sjaj

Opis

Visokokvalitetna emajl boja za metalne površine. Pogodna je za unutrašnju i spoljašnju upotrebu. ISOLAC DUCO karakteriše visoka čvrstoća, visok sjaj i visoka pokrivna moć. Ima odličnu otpornost na vremenske uslove i starenje. Brzo se suši i nudi jaku otpornost na habanje.

Primena

ISOLAC DUCO se može koristiti unutra i spolja, na novim i starim metalnim površinama, metalnim ogradama, mašinama i alatima.

Tehnički podaci

Boja:	bela, crna (0,375 l, 0.75 l & 2.5 l), 12 standardnih boja iz ISOLAC DUCO ton karte (0.375 l & 0.75 l) i izabrane nijanse boja iz ISOMAT COLOR SYSTEM ton kare i RAL nijansi boja (0.75 l & 2.5 l)
Tip:	alkidna emajl boja
Gustina:	0,96-1,20 kg/l
Neprozirnost:	min 97 %
Belina:	min 88 %
Prionjivost:	2,0 N/mm ²
Viskozitet (mPa.s):	3.000 na 23 °C
Vreme sušenja:	3-4 h (na dodir)
Sledeći sloj nakon:	24 h

Čišćenje alata:

Ukloniti što je više moguće boje sa korišćenog alata pre čišćenja. Alat očistiti temeljno sa SM-16 ili SM-18 odmah nakon upotrebe.

Uputstvo za upotrebu

1. Podloga

Podloga mora biti suva, bez masnoća, trošnih delova, prašine itd. Ako je potrebno finom šmirglom otkloniti sve nepravilnosti podloge. Zatim, prajmerisati ISOMAT RUST PRIMER-om.

2. Nanošenje

Pre upotrebe sadržaj ISOLAC DUCO-a, lagano promešati i naneti u dva sloja, razređena sa do 5% SM-18 za nanošenje četkom ili valjkom i sa do 10-20% SM-16 za nanošenje u spreju.

Drugi sloj naneti tek pošto se prvi u potpunosti osuši, otprilike nakon 24 sata. Temperatura tokom nanošenja i sušenja boje treba biti između +10 °C i +35 °C.

Pokrivna moć

ISOLAC DUCO pokriva 15 m²/l po premazu, na unapred pripremljenoj podlozi.

Pakovanje

ISOLAC DUCO je dostupan u kantama od 0,375 l, 0,75 l i 2,5 l.


Skladištenje – Rok upotrebe

24 meseci od datuma proizvodnje ako se čuva u originalnom, neotvorenom pakovanju na temperaturi između +5°C i +35°C. Zaštiti od direktne sunčeve svetlosti i smrzavanja.

Ispariva organska jedinjenja (VOC)

Maksimalna dozvoljena vrednost sadržaja VOC za ovaj proizvod (A/z) je 500g/l. Ovaj proizvod sadrži <500g/l.

ISOLAC DUCO

 2032
ISOMAT S.A. 17 th km Thessaloniki – Ag. Athanasios P.O. BOX 1043, 570 03 Ag Athanasios, Greece 18
2032-CPR-10.11 DoP No.: ISOLAC DUCO / 1439-01 EN 1504-2 Surface protection products Coating Permeability to CO ₂ : Sd > 50m Water vapor permeability: Class I (permeable) Capillary absorption: $w < 0.1 \text{ kg/m}^2 \cdot \text{h}^{0.5}$ Adhesion: $\geq 0.8 \text{ N/mm}^2$ Reaction to fire: Euroclass F Dangerous substances comply with 5.3

ISOMAT S.A.
BUILDING CHEMICALS AND MORTARS
MAIN OFFICES - FACTORY:
17th km Thessaloniki - Ag. Athanasios Road,
P.O. BOX 1043, 570 03 Ag. Athanasios, Greece,
Tel.: +30 2310 576 000, Fax: +30 2310 722 475
www.isomat.rs e-mail: info@isomat.rs