

Tehnički opis

ISOLAC RUST-PRIMER



Prajmer za metalne površine, protiv rđe

Opis

Prajmer za metalne površine, protiv rđe. Pogodan je za unutrašnju i spoljašnju upotrebu. Pruža odlično prijanjanje za podlogu i efikasno štiti metalne površine od rđe.

Primena

Koristi se na novim i starim površinama (vrata, gelenderi, mašine i alati) i predstavlja idealnu podlogu za emajl boju ISOLAC DUCO.

Tehnički podaci

Boja: siva, braon
Tip: alkidni prajmer
Gustina: 1.40 kg/l
Adhezija: 2.0 N/mm²
Viskozitet (mPa.s): 1,700 na 23 °C
Vreme sušenja: 1 h (na dodir)

Ponovno premazivanje: 8 h

Čišćenje alata:

Pre čišćenja, ukloniti što je više moguće materijala sa korišćenog alata. Alat temeljno očistiti sredstvom SM-16 ili SM-18, odmah nakon upotrebe.

Uputstvo za upotrebu

1. Priprema podloge

Metalna površina treba biti suva, bez rđe, masnoća, trošnih delova ili boje, prašine i sl., a sve nepravilnosti uglačati šmirglom.

2. Nanošenje

ISOLAC RUST-PRIMER naneti u jedan ili dva sloja, razređena sa 5-10% SM-18 za nanošenje četkom ili valjkom, ili sa 10-20% SM-16 za nanošenje u spreju.

Drugi sloj naneti tek pošto se prvi u potpunosti osuši, otprilike nakon 8 sati. Kada se drugi sloj osuši, može se uglačati šmirglom za bolje prijanjanje finalne boje. Temperatura tokom primene i sušenja prajmera treba biti između +10°C i +35°C.

Pokrivna moć

ISOLAC RUST-PRIMER pokriva do 13 m²/l po premazu, na unapred pripremljenoj površini.

Pakovanje

ISOLAC RUST-PRIMER je dostupan u kantama od 0.75 l i 2.5 l.

Skladištenje – Rok upotrebe

24 meseca od datuma proizvodnje ukoliko se čuva u originalnom, neotvorenom pakovanju na temperature između +5°C i +35°C. Zaštititi od direktne sunčeve svetlosti i mraza.

Ispariva organska jedinjenja (VOCs)

U skladu sa Direktivom 2004/42/CE (Aneks II, tabela A), maksimalni dozvoljeni VOC sadržaj za proizvod potkategorije i, tip SB je 500 g/l (2010) za gotov proizvod.

Gotov proizvod ISOLAC RUST-PRIMER sadrži maksimum 500 g/l VOC.

ISOMAT S.A.

BUILDING CHEMICALS AND MORTARS

MAIN OFFICES - FACTORY:

17th km Thessaloniki - Ag. Athanasios Road,
P.O. BOX 1043, 570 03 Ag. Athanasios, Greece,
Tel.: +30 2310 576 000, Fax: +30 2310 722 475

www.isomat.net e-mail: info@isomat.net

The technical information and instructions supplied in this datasheet are based on the knowledge and experience of the Department of Research and Development of our company and on results from long-term applications of the product in practice. The recommendations and suggestions referring to the use of the product are provided without guarantee, since site conditions during the applications are beyond the control of our company. Therefore the user is responsible for confirming that the chosen product is suitable for the envisaged application. The present edition of this technical datasheet automatically cancels any previous one concerning the same product.

